

Chemical Resistance

| Substance Organic chemicals | Concentration (%) | Temperature up to ... °C | PVC | | | | | | | | | | | | PE | PUR | H | Silicone | Neoprene Rubber | HELU FLON® |
|--------------------------------|-------------------|--------------------------|--|---|---------------------|---|---|--|--|--|--|---|---|--|---|---|--|----------|--------------------|---------------|
| | | | JZ-500/600/750 JB, QZ-BL, JZ-HF PVC-Flat, TRONIC (IYY), SUPERTRONIC-PVC | JZ-603, JZ 603-CY, Li-TPC-Y, PAAR-CY-QZ, N05W5-F, CE/20-22 | H05W5-F, H05WCAY5-K | LifY, Trago, Lift-2S, BAUFLEX BUS-cables-PVC, DAT-cables-PVC | JZ-602, JZ-602-CY, TRONIC-CY, LiYCY, JZ-602 RC, PAAR-TRONIC-CY, SY-JZ, SY-JB, JZ-602 RC-CY | F-CY-JZ, Y-CY-JZ, JZ-HF-CY, J-Y(ST)Y, J-YY, JE-Y(ST)Y S-YY, S-Y(ST)Y, TOPFLEX-PVC | ESUY, LifY, PVC-Single cores, EDV-PIMF-CY ESY, LiFDY, TUBEFLEx-CY | H 05 V-K, H 07 V-K, H 03 W-F, H 05 W-F | THERM 120, THERM 105, H05V2-K, H07V2-K | Coaxial-Cable (PE), L2-BUS-cable (PE) A-2Y(L2Y, A-2YFLU2Y, HELUCOM® ... 2Y | PUR-JZ, PUR-JZ-HF, TOPFLEX-PUR, ROBOFLEX, SUPERTRONIC-PUR, MULTIFLEX-PUR, TOPSERV® | J-HSDH Security Cable .E 30/E 90, HELUCOM-H JZ-500-HMH/MXMH, N2KH, H072-K, RG-H | SHF/SHF/QL-P, SHF, SID, SIFF, SIF/QL, SID/QL, SIHF-C-SI, FZ-I-S, FZ-LSI, N20MH2G | Neopren-Round/Flat, NSHTÖU, AIRPORT 400 Hz H01N2-D/E, H 05/H 07-, A 05/A 07 RN-F | FEP-6Y, PTFE-5Y, Compensating cables-FEP | | | |
| Aceton | 20 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ● | ● | ● | ● | ● | |
| Formic acid | 30 | 20 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ● | ○ | ● | ● | ● | ● | |
| Aniline | 50 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ● | ● | ● | |
| Petrol | 20 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ● ¹⁾ | ○ | ● | ○ | ● | |
| Benzene | 50 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ● | |
| Succinic acid, wat. | colds. | 20 | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | | | | | | |
| Brake fluid | 100 | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ○ | | | | | |
| Butane | 20 | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | |
| Butter | 50 | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | |
| Chlorobenzene | 30 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | |
| Chloroprene | 20 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | |
| Diethylether | 20 | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | |
| Diethylprestone | 50 | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | |
| Diesel oil | | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ● | ○ | ● | ● | ● | |
| Glacial acetic acid | 20 | 50 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ● | ● | ● | |
| Acetic acid | 20 | | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ○ | ○ | ● | ● | |
| Ethyl alcohol | 100 | 20 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ● | ● | ○ | ● | ● | |
| Ethyl chloride | 50 | | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ● | ● | ● | |
| Ethylene glycol | 100 | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | |
| Freon | 20 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ● | ○ | ○ | | | |
| Gear oil | 100 | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | |
| Glycerin | each | 50 | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | |
| Hydraulic oil | 20 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ●* | ○ | ○ | ○ | ● | |
| Isopropyl alcohol | 100 | 20 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ● | ●* | ● | ● | ● | |
| Kerosene | 20 | | | | | | | | | | | | | | ● | | | | | |
| Machine oil | 20 | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | |
| Methanol | 20 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ● | | ● | | |
| Methyl alcohol | 100 | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | |
| Methylen chloride | 20 | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | | |
| Lactic acid | 10 | | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ● | | |
| Mineral oil | | | | | | | | | | | | | | | ●* | | | | | |
| Motor oil | 120 | ○ | ● | ● | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ● | ● | ● | ● | |
| Olive oil | 50 | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | |
| Oxal acid | colds. | 20 | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | |
| Paraffin oil | | | | | | | | | | | | | | | ● | | | | | |
| Vegetable oils | | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | |
| Vegetable fats | | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | |
| Cutting oil | | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ●* | ○ | ● | ● | ● | |
| Tar acid | 20 | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ○ | | | | | |
| Carbon tetrachloride | 100 | 20 | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ○ | | | | | |
| Toluene | | | | | | | | | | | | | | | | | | | | |
| Trichloroethylene | 100 | 20 | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | |
| Tartaric acid, wat. | | | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | |
| Citric acid | | | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | |

- resistant
- conditionally resistant
- not resistant
- * for individual case, please verify
- ¹⁾ PUR-material is resistant

each = each concentration
colds. = cold saturated
wat. = watery, liquid

The information mentioned in this summary is given to the best of our own knowledge and based upon our long standing experience. But we would like to direct your attention to the fact, that the information is given without obligation. A final judgement can only be made in practice.

X